


MorKlad™

SelfSeal Weather Barrier

The Morin MorKlad™ SelfSeal Weather Barrier is a high-performance 2-in-1 solution that combines an air barrier and water-resistive barrier with the speed and simplicity of peel-and-stick installation. Its high-tack acrylic adhesive bonds securely to a wide range of substrates, reducing the need for mechanical fasteners while helping maintain a continuous building envelope. If misapplied or stuck to itself during installation, the wrap can be easily separated, repositioned, and reapplied without damaging the membrane or compromising performance.



- 9-month UV exposure
- Installs from 0°F to 150°F without compromising adhesion
- Primer-free adhesion with broad sealant compatibility
- AAMA 711 Compliance

Product Data

General		
Property	Test Method	Value
Water Penetration Resistance (CM H ₂ O)	AATCC-127	Pass
Air Permeance (L/s/m ² @ 75 Pa) (cfm/ft ² @ 1.57 psf)	ASTM E 2178	<0.02 <0.004
Tensile Strength (lbs/in., MD/TD)	ASTM D 882	39/34
Trapezoid Tearing Strength (lbs/in., MD/TD)	ASTM D 4533	57/68
Water Vapor Permeance (perms)	ASTM E96 Desiccant - Method A	20
U.V. Stability (Months)		9
Nominal Thickness(in./mils)		0.017 /17
Weight (lb/1000 ft ²)		94
Flame Spread	ASTM E 84	0
Smoke Developed	ASTM E 84	100
Fire Class	Class A	Class A

Handling & Storage

Store boxes containing MorKlad® SelfSeal Weather Barrier in a clean, dry area without prolonged, direct exposure to sunlight before installation.

Warnings

This product is combustible. A protective barrier or thermal barrier is required as specified in the appropriate building code. Protect it from exposure to open flame or other ignition sources during shipping, storage and installation.

The release paper of MorKlad™ SelfSeal Weather Barrier is slippery and should not be walked on at any time. Discard release paper in a designated container.

For more information on specific building product recommendations and installation guidelines, contact your Morin representative.



For the latest product information please visit www.morincorp.com
Care has been taken to ensure that the contents of this publication are accurate, but Morin Corporation does not accept responsibility for errors or information that is found to be misleading. Suggestions for, or description of, the end use or application of products or methods of working are for information only and Morin Corporation accepts no liability in respect thereof.

September 22, 2026

Morin®
By Kingspan